

Appl. No. : 10/019,753  
Filed : March 5, 2002

**AMENDMENTS TO THE SPECIFICATION**

Please correct the heading at page 54, line 1 as follows:

COMPARATIVE EXAMPLE 10

Please correct Table 2 on page 57 as follows:

Table 2

item	unit	Comparative-Example 10		Comparative Example 1	
		Polymer A	Polymer B	Polymer A	Polymer B
Molecular weight (Mw)	g/mol	2200	200000	7500	200000
Mixing ratio	% by weight	40	60	95	5
Antioxidant E	% by weight	0		0	
Silicone amount D	% by weight	0		0	
Fluidity (MI)	g/10 minutes	13		12	
Water absorption	%	0.10		0.08	
Heat resistance (Tg)	°C	121		142	
Relative permittivity	-	2.3		2.3	
Bending strength	Mpa	80		48	
Transparency	%	85		85	
Birefringence	-	$5 \times 10^{-5}$		Could not be measured	
Change in hue	-	0.28		0.29	



RECEIVED  
NOV 26 2003  
TC 1700